

Colour	Product	Precious Metal Content	Glass	Lead Crystal (firing temperature max. 540°C/1004°F)	Coated Glass	Notes*
light yellow	GGP 2093	8,5+10+12%	●	●		suitable for low firing temperatures on lead crystal, suitable for the decorating system Gold-on-White and Gold-on-Flux
light yellow	GGP 2148	12%	●	●		especially suitable for lead crystal
light yellow	GGP 2046	10%	●	●		wide firing range up to 750°C/1380°F, suitable for Heat-Release
yellow	GGP 2027	10+12%	●	●		very compatible on various glass compositions, suitable for the decorating system Gold-on-Flux
yellow	GGP 2032	11%	●			suitable for the decorating system Gold-on-Flux
yellow	GGP 2124	10%	●			high viscosity, suitable for the decorating system Gold-on-White
yellow	GGP 2027/3	8+10%	●	●		high viscosity, suitable for the decorating system Gold-on-Flux
reddish yellow	GGP 2121	7%	●			-
copper	GGP 2067	7,4%	●			-
rose	GGP 2052	8%	●			suitable for the decorating system Gold-on-White

These products may contain silver.

* For further information please refer to "Definitions"