

Colour	Product	Precious Metal Content	ASTM-resistant	microwave-resistant	Sanitary Ware	Notes*
light yellow	GGP 2538	12%				bright gold paste, lemon yellow firing result, wide firing range, very scratch-resistant, suitable for the Heraeus "silk matt gold system"
light yellow	GGP 1215	10+12%				lemon yellow firing result, suitable for the Heraeus "silk matt gold system"
light yellow	GGP 1213	10+12%				suitable for the Heraeus "silk matt gold system"
light yellow	GGP 2538	10%				wide firing range, very scratch-resistant, suitable for the Heraeus "silk matt gold system"
yellow	GGP 2536	10%				wide firing range, very scratch-resistant, suitable for the Heraeus "silk matt gold system"
yellow	GGP 2552	10%				suitable for the Heraeus "gold-under-flux-system"
yellow	GGP 2567	7%				-
yellow	GGP 2569					firing stable up to max. 820°C / 1508°F
yellow	GGP 2570					-
yellow	GGP 2571	12%	●			excellent chemical resistance (ASTM, Calgonite, dishwasher)
yellow	GGP 2572	10%	●			excellent chemical resistance (ASTM, Calgonite, dishwasher), suitable for the Heraeus "silk matt gold system"
reddish yellow	GGP 1220	10+12%				suitable for the Heraeus "silk matt gold system"

Colour	Product	Precious Metal Content	ASTM-resistant	microwave-resistant	Sanitary Ware	Notes*
reddish yellow	GGP 2555	12%	●			excellent chemical resistance (ASTM, Calgonite, dishwasher)
reddish yellow	GGP 2386/HT	10%				high temperature bright gold paste, firing range 900-1180°C/1650-2155°F
reddish yellow	GGP 2516/MW	9%		●		very scratch-resistant
reddish yellow	GGP 1220	8%				-
reddish yellow	GGP 2565	7%				-
reddish yellow	GGP 2531/MW	7%		●		very scratch-resistant

\* For further information please refer to "Definitions"